

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification: C08F 2/26	A1	(11) International Publication Number: WO 95/06070 (43) International Publication Date: 2 March 1995 (02.03.95)
(21) International Application Number: PCT/GB94/01814 (22) International Filing Date: 19 August 1994 (19.08.94) (30) Priority Data: 9317478.7 23 August 1993 (23.08.93) GB (71) Applicant (for all designated States except US): IMPERIAL CHEMICAL INDUSTRIES PLC [GB/GB]; Imperial Chemical House, Millbank, London SW1P 3JF (GB). (72) Inventor; and (75) Inventor/Applicant (for US only): SLEEGERS, Mark, Joannes, Ludovicus [BE/BE]; Kardinaal Cardijnlaan 76, B-2547 Lint (BE). (74) Agents: ROBERTS, Jonathan, Winstanley et al.; ICI Chemicals & Polymers Limited, Intellectual Property Dept., P.O. Box 11, The Heath, Runcom, Cheshire WA7 4QE (GB).		(81) Designated States: AU, CA, JP, NZ, US, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: SURFACTANTS (57) Abstract Oil-in-water emulsion polymerisation carried out in the presence of emulsifiers that are polyoxyethylene half ester of vic-dicarboxylic acids give latices that are stable especially to coagulation by electrolytes, shear and/or freezing. Particularly suitable emulsifiers are of the formulae (I): $Y.OOC.(HR)C.C(HR^1).COO.(AO)_n.R^2$ or (II) $Y.OOC.(HR)C.C(HR^1).COO.(AO)_n.CO.(HR^1)C.C(HR)COO.Y$ where: R, R ¹ , AO, n, R ² and Y are as defined, in particular where the emulsifiers are polyoxyethylene half esters of alkenyl succinic acids.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

- 1 -

SURFACTANTS

This invention relates to an oil-in-water emulsion polymerisation process carried out in the presence of a particular surfactants, especially vic-dicarboxylic acid polyalkyleneoxy half esters.

PCT application No PCT/GB 93/01335 published as WO 94/000508 A, describes a class of derivatives, particularly esters, of vicinal dicarboxylic acids, particularly alkenyl or alkyl substituted succinic acids. Various uses of these are described, for example as emulsifying agents. We have now found a sub-class of the compounds described in the PCT Application are particularly useful as oil-in-water emulsifying agents in the polymerisation of ethylenic monomers.

Accordingly, the invention provides a process of oil-in-water emulsion polymerisation is characterised by the presence of at least one polyoxyethylene half ester of a vic-dicarboxylic acid.

More particularly, the invention provides a process of oil-in-water emulsion polymerisation in which the oil phase includes at least one ethylenically unsaturated monomer to be polymerised wherein the emulsion is stabilised by one or more compounds of the formula (I) or (II):



where

one of R and R¹ is C₈ to C₂₂ alkenyl or alkyl and the other is hydrogen;

(AO)_n represents a polyalkylene oxide chain of units AO, of the formula -(C_mH_{2m}O)- where m is 2 or 3 (and may vary along the chain), which includes ethylene oxide units and which may include up to 50 mole % of propylene oxide units;


n is 8 to 100 (and as it is an average it may be non-integral);

R² is hydrogen or C₁ to C₆ alkyl; and

Y is a cation forming group, particularly H, alkali metal especially sodium or potassium, or ammonium (especially NH₄, amine ammonium or alkanolamine ammonium);

- 2 -

or



where:

n, AO each pair of R and R¹, and Y are independently as defined above for formula (I).

In the formulae (I) and (II) above the following represent particularly useful materials as emulsifiers in the process of this invention.

The group R or R¹ which is not hydrogen alkenyl or alkyl is very desirably a C₁₂ to C₁₆ alkenyl or alkyl, especially alkenyl, group. When the group R² is C₁ to C₆ alkyl it is desirably a methyl, ethyl, propyl, or butyl group, particularly a methyl group. Y is a cation forming group i.e. a group that can ionise from the rest of the molecule to form a cation thus leaving the residue of the molecule anionic i.e. negatively charged. In particular, it is hydrogen, alkali metal, especially sodium or potassium, or ammonium, especially NH₄, amine ammonium or alkanolamine ammonium.

The alkylene oxide chain represented by (AO)_n is of units AO of the formula -(C_mH_{2m}O)- where m is 2 or 3 (and may vary along the chain) includes ethylene oxide units and desirably is polyethylene oxide chain i.e. the group AO is -(CH₂.CH₂O)-. However, the chain may include a minor molar proportion of propylene oxide residues -(C₃H₆O)-. When the chain includes propylene oxide residues then these residues are desirably present as a block at the end of the alkylene oxide chain adjacent the carboxyl function. The number of alkylene oxide residues in the chain is from 8 to 100, particularly from 12 to 50, including polyethylene glycol (polyethylene oxide chains - PEG) chains equivalent to PEG 600 to PEG 2000.

Preferred emulsifiers used in this invention are generally as set out in our co-pending application, but the process especially employs such half esters containing anionic groups and/or groups ionisable to form an anion. Preferred emulsifiers used in the present invention contain anionically ionisable groups.

The polymerisation reaction mixture may include materials such as one or more other surfactants, such as alkyl phenol ethoxylates,

- 3 -

alcohol ethoxylates and their sulphate or phosphate esters; alkyl and aralkyl sulphonates; alcohol sulphates; sulphosuccinate mono- and diesters; alkylene oxide block copolymers, such as ethylene oxide propylene oxide copolymers; and end carboxylated ethoxylates (ether carboxylates); and/or protective colloids, such as water soluble cellulose ethers, e.g. carboxymethyl cellulose and hydroxyethyl cellulose; polyvinyl alcohol; and gums, such as xanthan and guar gums.

The oil-in-water emulsion polymerisation process of this invention can be carried out at pH values over a wide range, for example 3 to 11, particularly 4 to 10 especially 4 to 5 or 9 to 10.

The latex formed by the polymerisation is capable of high stability to electrolytes, shear and/or freezing, in particular against coagulation by such factors in uses where it is required to resist coagulation.

The monomers (co)polymerisable in the process of this invention include acrylic species such as acrylate and (alpha alkyl) acrylate esters; acrylonitrile; and water insoluble (alpha alkyl) acrylamides, including cationic and quaternary species; vinylic species, such as vinyl chloride, vinyl esters, vinyl ethers, vinyl pyridines and styrenes; other olefinic species, such as ethylene, propylene, butadiene, isoprene, isobutadiene, and chloroprene; and vicinal dicarboxylic acids and their ethers anhydrides, amides and imides. Acrylic monomers are particularly desirable as latices from acrylic monomers show particularly good freeze thaw stability when made by the process of this invention.

This list of monomers which are (co)polymerisable in the process includes species, such as isoprene, butadiene, isobutadiene, chloroprene, styrenes, and acrylonitrile and accordingly, the process of oil-in-water emulsion polymerisation according to this invention may be used in the production of emulsion rubber latices, including those of styrene butadiene rubbers (SBR), acrylonitrile butadiene rubbers (NBR), isoprene rubbers, isobutadiene rubbers and chloroprene rubbers.

The polymerisation catalyst in the process in general may be any conventional emulsion polymerisation catalyst compatible with the presence of the vic-dicarboxylic acid polyalkyleneoxy half ester, for example a peroxidic compound such as a persulphate.

- 4 -

The following Examples illustrate the invention. All parts and percentages are by weight unless otherwise stated.

Materials

Emulsifiers A to E are control emulsifiers included for comparison

- A - Rhodapex CO 436 sulphated ethoxylated nonylphenol with an average of 4 moles ethylene oxide - ex Rhone Poulenc
- B - Rhodapex EP110 sulphated ethoxylated nonylphenol with an average of 9 moles ethylene oxide - ex Rhone Poulenc
- C - Atpol HM935 sulphosuccinate half ester surfactant ex ICI
- D - Atlas G-3300B ex ICI

Emulsifiers A to D are commercially available materials, which contain anionically ionisable groups, used in emulsion polymerisation.

- E - Synperonic NP13 - an ethoxylated nonyl phenol with an average of 13 moles ethylene oxide - ex ICI

Emulsifiers F1 to F5 are materials used in this invention and are of the formula: $\text{H.OOC} \cdot (\text{HR}) \text{C} \cdot \text{C}(\text{HR}^1) \cdot \text{COO} \cdot (\text{CH}_2 \cdot \text{CH}_2\text{O})_n \cdot \text{H}$

where: one of R and R^1 is an alkenyl group (as given below) and the other is hydrogen and n is as given below

	R/ R^1	n (on average)
F1	C ₁₄ alkenyl	13.6
F2	C ₁₂ alkenyl	13.6
F3	C ₁₂ alkenyl	9
F4	C ₁₈ alkenyl	13.6
F5	C ₁₈ alkenyl	22.6
F6	C ₁₂ alkenyl	16
F7	C ₁₄ alkenyl	22
F8	C ₁₆ alkenyl	12
F9	C ₁₆ alkenyl	16

- 5 -

Test methods

Viscosity (Visc.)

is Brookfield viscosity measured using spindle 4 at speed 2, results are quoted in mPas.

Particle Size (Size)

for Examples 1 and 3 was measured using a Malvern Zetasizer, and for Example 2 using a Malvern Mastersizer. The mean particle size is quoted in nm

Electrolyte Stability (ES)

Equal quantities of polymer emulsion and 5% w/w calcium chloride solution were thoroughly mixed and then allowed to stand for 24 hours after which the stability was assessed.

Shear Stability (SS)

the latex was subject to shearing using a rotating Diaf dissolver disc at 50 Hz for 30 minutes. The latex was assessed one day and one week after the exposure to shear.

Freeze-thaw Stability (FTS)

A sample of neutralised latex was cooled to -20°C over 1 hour held at this temperature for 11 hours, heated to +23°C over 1 hour and held at this temperature for 11 hours. This cycle was repeated 5 times and the final result evaluated.

The results for Electrolyte Stability Shear Stability and Freeze-thaw Stability are based on the following assessment criteria:

good - no sign of individually visible particles
fair - latex appearance retained, but visible particles formed
fail - large flocs formed

- 6 -

Example 1

The Oil-in-water emulsion polymerisation of butyl acrylate / methyl methacrylate/maleic anhydride (48.8 : 49.9 : 1.3 by weight).

A polymerisation reactor was charged with the following:

demineralised water	165.5 g
sodium persulphate	0.5 g
emulsifier	15 g
Monomer charge	51 g

The reactor was purged with nitrogen gas for 5 minutes and then heated to 85°C and held at that temperature for 5 minutes. The following two streams were then fed to it simultaneously while holding the temperature at 85°C:

- a) over 2 hours monomer mixture 462 g
- b) over 2 hours 15 minutes a solution of
 - sodium persulphate 1.3 g
 - in demineralised water 46.7 g

After the monomer addition was complete, the reaction mixture was held over another 2 h at 85°C to ensure minimal residual monomer levels. The resulting latex was allowed to cool, neutralised with aqueous ammonia (as NH_4OH) to $\text{pH } 9.4 \pm 0.2$, then bottled for storage. Table 1 below shows a selection of properties of the latices produced.

Example 2

The oil-in-water emulsion polymerisation of vinyl acetate / butyl acrylate (85:15 molar)

A polymerisation reactor was charged with the following:

- 7 -

demineralised water	403.75 g
Natrosol 250MR	2.75 g
(hydroxyethyl cellulose)	
sodium bicarbonate	2.00 g
sodium persulphate	0.5 g
emulsifier	15.0 g

The reactor was purged for 20 minutes with nitrogen gas, heated to 75°C and held at that temperature for 15 minutes. The following two streams were then fed to it simultaneously (as in Example 1), while holding the temperature at 75°C.

- a) over 2 hours monomer mixture 462 g
- b) over 2 hours 15 minutes a solution of:
 - sodium persulphate 1.3 g
 - in demineralised water 46.7 g

After the monomer addition was complete, the reaction mixture was held over another 2 h at 75°C to ensure minimal residual monomer levels. The resulting latex was allowed to cool, then bottled for storage. Table 2 below shows a selection of the properties of the latices produced.

Example 3

The oil-in-water polymerisation of butyl acrylate / methyl methacrylate / methacrylic acid (136.8:140:3.5 by weight)

A butyl acrylate / methyl methacrylate / methacrylic acid latex was made at a nominal solids content of 38% by a seeded semi-continuous method. A polymerisation reactor was charged with the following:

demineralised water	417.1 g
sodium persulphate	0.25 g
emulsifier	6.9 g
monomer charge	7.5 g

- 8 -

Two feeds were made up with following composition:

monomer feed	272.6 g
initiator feed	
sodium persulphate	0.5 g
demineralised water	45.0 g

The reactor charge and monomer feed were purged with nitrogen for 20 minutes. The reactor charge was then heated to 85°C and held at this temperature for 5 minutes. The monomer feed and the initiator feed were then simultaneously added to the reactor charge in two streams; the monomer feed over 2 hours and the initiator feed for the 2 hours and a further 15 minutes. The reactor mixture was then held at 85°C for a further 2 hours after which the latex was allowed to cool. The pH and particle size of this latex were measured on this acidic latex. The remainder of the latex was neutralised to pH 9.4 \pm 0.2 and was then bottled for storage. Further measurement of particle size and pH and the remaining tests were carried out on the neutralised latex. The results of the testing are set out in Table 3 below.

Table 1

Emul.	Visc. (mPas)	pH	Size (nm)	ES	SS	FTS
A	<100	9.3	-	fail	good	fail
B	< 100	9.4	73	fail	good	fail
C	< 100	9.6	76	fail	good	fail
D	-	-	-	-	-	-
E	900	9.5	120	good	fair	fail
F1	< 100	9.5	176	good	good	good
F2	< 100	9.4	202	good	good	good
F3	-	9.5	433	good	good	good
F4	-	9.4	218	good	good	good
F5	-	9.5	168	good	good	good

- 9 -

Table 2

Emul.	Visc. (mPas)	pH	Size (nm)	ES	SS	FTS
A	1000	4.5	620	good	good	fail
B	3200	4.6	-	good	fair	fail
C	100	5.3	1150	good	good	fail
F1	5200	4.4	1310	good	good	good
F2	1000	4.1	-	good	-	-
F3	200	4.6	1880	good	good	good
F4	1700	4.4	2270	good	fair	good
F5	700	4.3	1110	good	good	good

Table 3

Emuls.	Visc. (mPas)	pH		Particle size (nm)		ES	SS	FTS
		+	-	+	-			
A	<100	-	9.3	-	-	fail	good	fail
B	<100	-	9.4	-	72.7	fail	good	fail
E	<100	2.6	9.2	132.7	120.3	fail	sed	fail
F1	<100	2.4	9.2	185.7	189.2	good	good	good
F2	<100	-	9.4	-	201.9	good	good	good
F4	<100	2.3	9.2	165.0	218.2	good	good	good
F5	<100	2.3	9.2	164.0	167.8	good	t.cr	good
F6	<100	2.3	9.2	144.3	197.0	good	good	good
F7	<100	2.3	9.2	122.6	187.0	good	sed	good
F8	<100	2.4	9.2	162.5	208.4	good	good	good
F9	<100	2.3	9.2	123.1	173.3	good	fair	good

notes to Table 3

+ measurement before neutralisation
 - measurement after neutralisation
 sed some sediment formed
 t.cr slight creaming noted

- 10 -

Claims

- 1 A process of oil-in-water emulsion polymerisation characterised by the presence of at least one polyoxyethylene half ester of a vic-dicarboxylic acid.
- 2 A process as claimed in claim 1 in which the oil phase includes at least one ethylenically unsaturated monomer to be polymerised wherein the emulsion is stabilised by one or more compounds of the formula (I) or (II):



where

one of R and R^1 is C_{12} to C_{22} alkenyl or alkyl and the other is hydrogen;


$(AO)_n$ represents a polyalkylene oxide chain of units AO, of the formula $-(C_mH_{2m}O)-$ where m is 2 or 3 (and may vary along the chain), which includes ethylene oxide units and which may include up to 50 mole % of propylene oxide units;

n is 8 to 100;

R^2 is hydrogen or C_1 to C_6 alkyl; and

Y is a cation forming group;

or



where:

n, AO and each R, R^1 , and Y are independently as defined above for formula (I).

- 3 A process as claimed in claim 2 in which the group R or R^1 which is not hydrogen is a C_{12} to C_{16} alkenyl group; R^2 is hydrogen or a methyl, ethyl, propyl, or butyl group; Y is H, alkali metal, or ammonium; AO is $-CH_2.CH_2O-$; and n is from 12 to 50.
- 4 A process as claimed in any one of claims 1 to 3 which is the polymerisation or copolymerisation of one or more of acrylic

- 11 -

species, vinylic species, ethylene, propylene, butadiene, isoprene, isobutadiene, chloroprene and vicinal dicarboxylic acids and their ethers anhydrides, amides and imides.

- 5 A process as claimed in any one of claims 1 to 4 in which the polymerisation reaction mixture includes one or more other surfactants and/or protective colloids,

INTERNATIONAL SEARCH REPORT

International Application No
PCT/GB 94/01814

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 C08F2/26

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C08F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	FR,A,2 515 639 (THE KENDALL CO.) 6 May 1983 see claim 1 ---	1-5
X	BE,A,630 043 (UNIBASIC INC.) 15 July 1963 see claim 1 -----	1-5

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *Z* document member of the same patent family

Date of the actual completion of the international search

10 January 1995

Date of mailing of the international search report

24.01.95

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+31-70) 340-3016

Authorized officer

Cauwenberg, C

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/GB 94/01814

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
FR-A-2515639	06-05-83	BE-A- 894897	03-05-83
		CA-A- 1203810	29-04-86
		DE-A- 3240775	30-06-83
		GB-A, B 2111484	06-07-83
		JP-A- 58103505	20-06-83
<hr/>			
BE-A-630043		FR-A- 1360710	
<hr/>			

Form PCT/ISA/210 (patent family annex) (July 1992)